Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently amended) A polyolefin woven fabric extrusion coating [with superior soft tactile characteristic] comprising:

   from 30 to 50% by weight thermoplastic vulcanizate wherein the thermoplastic vulcanizate has a Shore A hardness grade of 30 to 80; and

   from 30 to 50% by weight of polyolefin elastomer wherein the polyolefin elastomer has a melt index of less than or equal 5.0.

2. (Original) The polyolefin woven fabric extrusion coating of claim 1 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

3. (Currently amended) ~~A~~ The polyolefin woven fabric extrusion coating ~~with superior soft tactile characteristic~~ of claim 1 further comprising:

   ~~from 30 to 50% by weight thermoplastic vulcanizate wherein the thermoplastic vulcanizate has a Shore A hardness grade of 30 to 80;~~

   ~~from 30 to 50% by weight of polyolefin elastomer wherein the polyolefin elastomer has a melt index of less than or equal 5.0; and~~

   from 5 to 15% by weight of plastomer.

4. (Original) The polyolefin woven fabric extrusion coating of claim 3 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

5. (Withdrawn) The method of forming a coated polyolefin fabric of superior soft tactile characteristic comprising:

   weaving a polyolefin fabric of multi-filament polyolefin yarn;

extrusion coating the lower surface of the polyolefin fabric with a polyolefin woven fabric extrusion coating with superior soft tactile characteristic;

extrusion coating the upper surface of the polyolefin fabric with a polyolefin woven fabric extrusion coating with superior soft tactile characteristic; and

cooling the coated polyolefin fabric;

wherein the polyolefin woven fabric extrusion coatings with superior soft tactile characteristic comprise from 30 to 50% by weight thermoplastic vulcanizate wherein the thermoplastic vulcanizate has a Shore A hardness grade of 30 to 80; from 30 to 50% by weight of polyolefin elastomer wherein the polyolefin elastomer has a melt index of less than or equal 5.0; and from 5 to 15% by weight of plastomer.

6. (Withdrawn) The method of claim 5 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

7. (Currently amended) A coated polyolefin fabric ~~of superior soft tactile characteristic~~ comprising:

an inner polyolefin fabric of multi-filament polyolefin yarn;

one or more lower coating layers of polyolefin woven fabric extrusion coating ~~with superior soft tactile characteristic~~;

one or more upper coating layers of polyolefin woven fabric extrusion coating ~~with superior soft tactile characteristic~~;

wherein the polyolefin woven fabric extrusion coatings [with superior soft tactile characteristic] comprise from 30 to 50% by weight thermoplastic vulcanizate wherein the thermoplastic vulcanizate has a Shore A hardness grade of 30 to 80; from 30 to 50% by weight of polyolefin elastomer wherein the polyolefin elastomer has a melt index of less than or equal 5.0; and from 5 to 15% by

weight of plastomer.

8. (Original) The coated polyolefin fabric of claim 7 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

9. (Currently amended) The coated polyolefin fabric ~~of superior soft tactile characteristic~~ of claim 7 wherein the inner polyolefin woven fabric further comprises polypropylene multi-filament yarn.

10. (Original) The coated polyolefin fabric of claim 9 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

11. (Currently amended) The coated polyolefin fabric [of superior soft tactile characteristic] of claim 9 wherein the inner polyolefin woven fabric comprises 1000 denier polypropylene yarn on a nominal 16 x 16 ppi weave.

12. (Original) The coated polyolefin fabric of claim 11 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

13. (Currently amended) The coated polyolefin fabric ~~of superior soft tactile characteristic~~ of claim 7 wherein the lower coating layers comprise a total coating thickness of from 1 to 10.0 mil.

14. (Original) The coated polyolefin fabric of claim 13 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.

15. (Currently amended) The coated polyolefin fabric ~~of superior soft tactile characteristic~~ of claim 7 wherein the upper coating layers comprise a total coating thickness of from 1 to 10.0 mil.

16. (Original) The coated polyolefin fabric of claim 15 wherein the thermoplastic vulcanizate has a Shore A hardness grade of 54 to 80.